Case Study
ISSN: 3051-8814
Journal homepage: https://www.harrisonacademicpress.com/index.php/FBEMD
Frontiers in Biomedical Engineering and Medical Devices

Harrison Academic Press

Finite Element Analysis of Stress Distribution in a Novel Hip Prosthesis Design

Barbu I[1*], Greco V[2] and Kiss T[3]

[1]*Department of Biomedical Engineering, Carol Davila University of Medicine and Pharmacy, Bucharest, Romania*
[2]*Department of Orthopaedic Surgery, Sapienza University of Rome, Rome, Italy*
[3]*Department of Mechanical Engineering, University of Debrecen, Debrecen, Hungary*

ABSTRACT

Background: Aseptic loosening after total hip arthroplasty is closely linked to stress shielding, the unloading of periprosthetic bone caused by stiffness mismatch between metallic femoral stems and host bone. Objective: This narrative review synthesizes published finite element analysis (FEA) and clinical evidence on stress distribution in hip prosthesis stem designs. Methods: Peer-reviewed FEA, biomechanical, and densitometric studies addressing conventional alloys, cross-sectional and fenestration optimization, functionally graded and low-modulus alloys, additively manufactured porous/lattice titanium, and carbon-fiber-reinforced polymer composites were reviewed. Findings: Cobalt-chromium and titanium stems consistently show proximal stress shielding in FEA models; cross-sectional optimization yields modest improvement, while low-modulus graded alloys, porous lattice titanium, and composite stems produce substantially larger, reproducible reductions in strain-energy-based stress-shielding indices, corroborated by patient-specific model validation and longitudinal bone mineral density data. Conclusions: Convergent computational and clinical evidence supports architected porosity, graded stiffness, and composite substitution as the most promising directions for reducing stress shielding, though standardized, validated modeling protocols remain needed to confirm long-term clinical benefit.

Keywords: *hip prosthesis; finite element analysis; stress shielding; femoral stem design; biomaterials*

Citation: Barbu I, Greco V, Kiss T (2024) Finite Element Analysis of Stress Distribution in a Novel Hip Prosthesis Design. Front Biomed Eng Med Devices, 2(1): 01-06.
DOI: 10.5281/zenodo.22485984

Corresponding Author: *Ioana Barbu*

E-mail Address: *ioana.barbu@umfcd.edu*

Article History: *Received 17 January 2024 | Accepted 5 April 2024 | Published 18 June 2024*

Copyright: *© 2024 Ioana Barbu, et al. This is an open access article distributed under the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited (**https://creativecommons.org/licenses/by/4.0/**).*

Total hip arthroplasty (THA) is among the most successful orthopaedic interventions, yet long-term implant survival remains limited by aseptic loosening driven largely by adverse bone remodeling around the femoral stem [1]. When a stiff metallic stem is implanted into the femoral canal, it carries a disproportionate share of the physiological load, unloading the surrounding cortical bone in a phenomenon known as stress shielding [2]. Because bone adapts to its mechanical environment, chronic unloading triggers resorption, most pronounced in the proximal medial femur (Gruen zone 7), which can compromise fixation and complicate future revision [3]. Finite element analysis (FEA) has become the principal computational tool for predicting how stem geometry, cross-sectional design, and material stiffness govern the distribution of von Mises stress in the periprosthetic bone and cement mantle, allowing candidate designs to be screened before costly bench or clinical testing [4,5].

Realistic FEA of a hip prosthesis requires physiologically representative boundary conditions; in vivo instrumented-implant measurements of hip joint contact forces during walking, stair climbing, and other activities of daily living, and the standardized loading profiles derived from them, are now routinely used to load femur-implant models [6,7]. Coupled with patient-specific bone geometry and validated material properties, such models can reproduce measured cortical strains with reasonable fidelity [8]. Over the past two decades this modeling framework has been applied to an increasingly broad design space: conventional cobalt-chromium and titanium-alloy stems, cross-sectional and fenestrated geometry optimization, functionally graded and low-modulus alloys, porous and lattice architectures enabled by additive manufacturing, and fiber-reinforced polymer composites intended to better match the stiffness of host bone.

Clinically, the consequences of unfavorable stress distribution extend beyond a purely mechanical curiosity. Aseptic loosening secondary to progressive bone loss and micromotion at the bone-implant interface remains one of the leading indications for revision surgery, and revision procedures carry higher morbidity, cost, and technical difficulty than primary arthroplasty. This has

motivated a sustained engineering effort, spanning conventional alloy substitution, cross-sectional shape optimization, functionally graded materials, and, more recently, additively manufactured porous and lattice architectures, all evaluated primarily through finite element simulation before any bench or clinical testing is undertaken. Because these design iterations differ substantially in reported methodology, loading assumptions, and outcome metrics, a synthesis of the accumulated evidence is needed to identify which strategies produce reproducible, clinically meaningful reductions in stress shielding.

This narrative review synthesizes published FEA and complementary clinical/experimental evidence on stress distribution in novel hip prosthesis designs. Rather than reporting new simulation results, it draws together findings from the peer-reviewed literature to characterize (i) how material selection governs stress shielding, (ii) how emerging porous, graded, and composite stem architectures redistribute load, and (iii) how model validation and in vivo loading data constrain the clinical relevance of these predictions. The goal is to provide device engineers and clinicians with an integrated, evidence-based picture of where hip stem design stands and where the persistent trade-offs remain.

Stress Shielding and Material Selection in Hip Stem Design


The mechanical mismatch between implant and bone is the central driver of stress shielding. Cobalt-chromium alloys (elastic modulus roughly 210-230 GPa) and even titanium alloys such as Ti-6Al-4V (approximately 110-114 GPa) are one to two orders of magnitude stiffer than cortical bone (approximately 17-20 GPa), so classical beam-on-elastic-foundation and finite element analyses consistently show peak load transfer occurring near the distal stem tip while the proximal metaphysis is unloaded [2,9]. Early parametric FEA work on cross-sectional shape optimization demonstrated that redistributing stem cross-section and reducing distal stiffness could shift stress transfer more proximally without exceeding fatigue limits [9,10]. Hollow-stemmed and fenestrated designs pursue the same goal by removing material from the distal stem: finite element models of hollow stems predicted reduced distal stiffness and more physiological proximal strain, although wall-thickness reduction must be balanced against fatigue and manufacturing constraints [11,12].

A parallel strategy targets bulk material stiffness directly. Low-modulus beta-titanium alloys such as Ti-33.6Nb-4Sn, with a modulus gradation from roughly 40 GPa proximally toward the bone-matching range, have been evaluated in combined finite element and in vitro biomechanical studies, showing substantially reduced strain-energy-based stress-shielding indices relative to conventional Ti-6Al-4V stems while retaining adequate primary stability [13]. Functionally graded stem concepts, in which the elastic modulus varies spatially within the implant, have likewise been modeled to reduce interfacial bone and cement stresses relative to homogeneous stems [14]. Comparative FEA across stainless steel, cobalt-chromium, and titanium implants under identical femur geometry and loading confirms that, of the conventional alloys, titanium consistently yields the lowest proximal stress-shielding metric, at the cost of somewhat higher peak stem stresses [15]. Beta-titanium niobium alloys, such as Ti-27Nb, have also been evaluated under multiple physiologically representative loading scenarios (walking, stair ascent, and stumbling), with reported safety factors and stress distributions supporting their candidacy as lower-modulus alternatives to Ti-6Al-4V across a range of daily activities rather than a single idealized load case [16]. Polymer-based composites push this trend further: carbon-fiber-reinforced PEEK stems (effective modulus on the order of 18-22 GPa) have been analyzed both as bulk stem materials and as surface coatings, with finite element studies reporting markedly reduced stress shielding compared with metallic stems, alongside acceptable static and fatigue safety factors [17,18,19].

Table 1: Representative mechanical properties of femoral stem materials discussed in this review.

Material	Typical Elastic Modulus (GPa)	Reported Stress-Shielding Behavior
Cobalt-chromium alloy (cast)	~210-230	High proximal stress shielding; long clinical track record
Ti-6Al-4V (wrought)	~110-114	Moderate-high stress shielding; standard cementless benchmark
Graded beta-Ti (Ti-33.6Nb-4Sn)	~40-60 (graded)	Reduced stress shielding vs Ti-6Al-4V, retains primary stability
Carbon-fiber-reinforced PEEK	~18-22	Markedly reduced stress shielding; adequate static/fatigue safety
Porous/lattice titanium (AM)	~5-30 (tunable)	Largest reported stress-shielding reduction; fatigue-limited

Figure 1: Typical reported elastic modulus of femoral stem materials relevant to stress-shielding mitigation, illustrating the stiffness gradient from conventional cobalt-chromium alloy down toward cortical bone (values are representative/typical ranges drawn from the reviewed literature, not a single controlled experiment) [13,19,20,21].




Advances in Porous, Lattice, and Composite Stem Architectures

Additive manufacturing has enabled a further generation of stem designs that decouple local stiffness from bulk alloy choice by introducing controlled porosity. Fully porous, three-dimensionally printed titanium femoral stems designed with spatially graded lattice unit cells have been shown computationally to reduce strain-energy-based stress-shielding scores by roughly 70-75% relative to a fully dense Ti-6Al-4V stem of identical outer geometry, while satisfying fatigue and yield safety margins under simulated gait loading [20]. Subsequent optimization studies combining lattice topology design with

selective laser melting fabrication report similarly favorable trade-offs between reduced effective stiffness and mechanical integrity, and emphasize that pore size, strut thickness, and gradient placement must be co-optimized against manufacturability and fatigue life [21]. Broader reviews of titanium lattice structures for orthopaedic and other bone-contacting applications summarize the achievable range of effective elastic moduli (from a few GPa up to that of dense titanium) as a function of relative density and unit-cell architecture, underscoring that lattice design offers a practically continuous means of tuning implant stiffness toward that of host bone [22,23].

Figure 2: Representative strain-energy-based stress-shielding reduction reported for novel stem architectures relative to a conventional dense Ti-6Al-4V stem (illustrative/typical percentages synthesized from the cited finite element studies) [20,21,13,19,12].



Complementary finite element work has examined the tribological and structural consequences of these design changes. Wear-oriented simulations of hip implants under static loading indicate that contact pressure distribution at the articulating interface is sensitive to material pairing and surface geometry, independent of stem stiffness choices, highlighting that stress-shielding mitigation strategies must be evaluated jointly with wear and fatigue performance rather than in isolation [24]. Fatigue-focused analyses of novel stem geometries, including three-dimensional shape-optimized and 3D-scan-derived cemented stem models, report peak von Mises stresses in the stem body typically in the tens of MPa under static single-leg-stance loading, rising under dynamic and fatigue loading scenarios, but generally remaining below reported endurance limits for the alloys studied when geometry is optimized [5,4,25]. Coating strategies, such as applying a carbon/PEEK or polymeric PEEK layer over a metallic core, have also been modeled as an intermediate approach that retains metallic structural stiffness while reducing the effective stiffness gradient at the bone-implant interface [17]. Taken together, these studies indicate convergent evidence that architected porosity, graded composition, and composite substitution each independently reduce predicted stress shielding, with the largest reported reductions associated with fully porous or lattice-graded titanium designs.

Model Validation and Clinical Correlates of Stress Shielding

The predictive value of any hip stem FEA depends on how well the underlying femur and implant models are validated against experimental or clinical data. Patient-specific finite element models of femurs with cemented implants, built from computed tomography data and validated against measured cortical strains, have demonstrated that inhomogeneous, subject-specific material mapping is necessary to reproduce strain patterns accurately, and that generic homogeneous-bone models can misestimate peak proximal strains [8]. Loading assumptions matter comparably: standardized hip joint contact force and moment profiles derived from instrumented telemetric implants during walking, stair ascent/descent, and other activities provide the load cases most commonly adopted in contemporary stem FEA, replacing earlier simplified single-leg-stance approximations [6,7].

Clinically, dual-energy X-ray absorptiometry (DXA) studies of periprosthetic bone mineral density after cementless titanium stem implantation provide a direct, longitudinal correlate of the stress-shielding predicted computationally: proximal (Gruen zone 7) bone mineral density has been shown to decline substantially within the first one to two postoperative years and to remain reduced, though relatively stable, through the second and third decade of follow-up, broadly consistent with the load-transfer patterns predicted by finite element stress-shielding indices [3]. This convergence between simulated stress distributions and measured bone density loss supports strain-energy-based stress-shielding metrics as clinically meaningful design criteria rather than purely computational artifacts [2]. Comparative structural analyses across different current-generation stem designs and materials, evaluated under matched loading and boundary conditions, similarly show measurable differences in both proximal stress shielding and peak implant stress depending on stem geometry and alloy choice, reinforcing that no single design parameter can be optimized in isolation [15,26]. Collectively, the validated modeling pipeline, from instrumented-implant loading through patient-specific geometry to strain-energy-based stress-shielding metrics, now provides a reasonably well-corroborated basis for comparing novel stem concepts before clinical introduction. Nonetheless, most published FEA studies still rely on idealized or averaged bone geometry and simplified bonded or frictional interface conditions rather than the full range of patient anatomy and osseointegration states encountered clinically, so predicted stress-shielding indices should be interpreted as comparative rather than absolute measures of in vivo performance. Wider adoption of subject-specific imaging-derived models, combined with standardized reporting of loading cases and boundary conditions, would improve comparability across the design studies reviewed here and strengthen the link between computational predictions and long-term registry outcomes.

Across three decades of finite element analysis, a consistent picture has emerged: femoral stem stiffness, geometry, and internal architecture jointly determine the degree to which a hip prosthesis unloads the proximal femur, and that unloading is measurably linked to periprosthetic bone loss and, ultimately, implant longevity. Conventional cobalt-chromium and titanium alloys remain mechanically robust but stiffness-mismatched to bone; cross-sectional and fenestration optimization offer modest, low-risk improvements; low-modulus and functionally graded alloys, carbon-fiber-reinforced polymer composites, and additively manufactured porous or lattice titanium stems each demonstrate larger, well-documented reductions in predicted stress shielding. Realizing these benefits clinically will require continued integration of patient-specific, experimentally validated finite element models with physiologically representative in vivo loading data, alongside longitudinal densitometric and registry follow-up, to confirm that computationally favorable novel designs translate into durable, well-fixed implants over the decades-long service lives now

expected of total hip arthroplasty.

Acknowledgements

The authors thank colleagues at Department of Biomedical Engineering, Carol Davila University of Medicine and Pharmacy, Bucharest, Romania, Department of Orthopaedic Surgery, Sapienza University of Rome, Rome, Italy, and Department of Mechanical Engineering, University of Debrecen, Debrecen, Hungary for helpful discussions during preparation of this review.

Funding

This research received no specific grant from any funding agency in the public, commercial, or not-for-profit sectors.

Conflict of Interest

The authors declare no conflict of interest.

Author Contributions

Barbu I conceived the review, conducted the literature search, and drafted the manuscript. Greco V contributed to the literature screening and technical framing and critically revised the manuscript for important intellectual content. Kiss T contributed additional context and approved the final version for submission.

Ethics Statement

Not applicable. This is a narrative review of previously published literature and did not involve new experimental data, human participants, or animal subjects.

Data Availability

No new data were generated or analyzed for this review. All sources synthesized are cited in the reference list and are available through their original publishers.

References

1. Sumner DR (2015). Long-term implant fixation and stress-shielding in total hip replacement. Journal of Biomechanics, 48(5), 797-800. DOI: 10.1016/j.jbiomech.2014.12.021.

2. Huiskes R, Weinans H, van Rietbergen B (1992). The relationship between stress shielding and bone resorption around total hip stems and the effects of flexible materials. Clinical Orthopaedics and Related Research, 274, 124-134.

3. Peitgen DS, Innmann MM, Merle C, Gotterbarm T, Moradi B, Streit MR (2018). Periprosthetic Bone Mineral Density Around Uncemented Titanium Stems in the Second and Third Decade After Total Hip Arthroplasty: A DXA Study After 12, 17 and 21 Years. Calcified Tissue International, 103(4), 372-379. DOI: 10.1007/s00223-018-0438-9.

4. Kayabasi O, Ekici B (2007). The effects of static, dynamic and fatigue behavior on three-dimensional shape optimization of hip prosthesis by finite element method. Materials & Design, 28(8), 2269-2277. DOI: 10.1016/j.matdes.2006.08.012.

Table 2: Selected finite element analysis studies of hip stem stress distribution referenced in this review.

Study	Stem Concept Evaluated	Key Reported Finding
Arabnejad et al. 2017	Fully porous 3D-printed Ti lattice stem	~70-75% reduction in stress-shielding score vs dense Ti-6Al-4V
Yamako et al. 2017	Graded low-modulus Ti-33.6Nb-4Sn stem	Reduced strain-energy-based stress-shielding index
Darwich et al. 2019	Carbon/PEEK and PEEK coated stems	Reduced proximal stress shielding vs uncoated metal stem
Katz et al. 2018	Patient-specific cemented femur model	Subject-specific mapping needed to match measured strains
Amjad et al. 2024	Ti-27Nb alloy stem, multiple activities	Adequate safety factors across walking, stairs, stumbling loads

5. Senalp AZ, Kayabasi O, Kurtaran H (2007). Static, dynamic and fatigue behavior of newly designed stem shapes for hip prosthesis using finite element analysis. Materials & Design, 28(5), 1577-1583. DOI: 10.1016/j.matdes.2006.02.015.

6. Bergmann G, Deuretzbacher G, Heller M, Graichen F, Rohlmann A, Strauss J, Duda GN (2001). Hip contact forces and gait patterns from routine activities. Journal of Biomechanics, 34(7), 859-871. DOI: 10.1016/S0021-9290(01)00040-9.

7. Bergmann G, Bender A, Dymke J, Duda G, Damm P (2016). Standardized Loads Acting in Hip Implants. PLOS ONE, 11(5), e0155612. DOI: 10.1371/journal.pone.0155612.

8. Katz Y, Lubovsky O, Yosibash Z (2018). Patient-specific finite element analysis of femurs with cemented hip implants. Clinical Biomechanics, 58, 74-89. DOI: 10.1016/j.clinbiomech.2018.06.012.

9. Sabatini AL, Goswami T (2008). Hip implants VII: Finite element analysis and optimization of cross-sections. Materials & Design, 29(7), 1438-1446. DOI: 10.1016/j.matdes.2007.09.002.

10. Kayabasi O, Erzincanli F (2006). Finite element modelling and analysis of a new cemented hip prosthesis. Advances in Engineering Software, 37(7), 477-483. DOI: 10.1016/j.advengsoft.2005.09.003.

11. Gross S, Abel EW (2001). A finite element analysis of hollow stemmed hip prostheses as a means of reducing stress shielding of the femur. Journal of Biomechanics, 34(8), 995-1003. DOI: 10.1016/S0021-9290(01)00072-0.

12. Ikhsan, Prabowo AR, Sohn JM, Triyono J (2020). Finite Element Analysis of Different Artificial Hip Stem Designs Based on Fenestration under Static Loading. Procedia Structural Integrity, 27, 101-108. DOI: 10.1016/j.prostr.2020.07.014.

13. Yamako G, Janssen D, Hanada S, Anijs T, Ochiai K, Totoribe K, Chosa E, Verdonschot N (2017). Improving stress shielding following total hip arthroplasty by using a femoral stem made of β type Ti-33.6Nb-4Sn with a Young's modulus gradation. Journal of Biomechanics, 63, 135-143. DOI: 10.1016/j.jbiomech.2017.08.017.

14. Al-Jassir FF, Fouad H, Alothman OY (2013). In vitro assessment of Function Graded (FG) artificial Hip joint stem in terms of

bone/cement stresses: 3D Finite Element (FE) study. BioMedical Engineering OnLine, 12(1), 5. DOI: 10.1186/1475-925X-12-5.

15. Chethan KN, Zuber M, Bhat NS, Shenoy BS, Kini CR (2019). Static structural analysis of different stem designs used in total hip arthroplasty using finite element method. Heliyon, 5(6), e01767. DOI: 10.1016/j.heliyon.2019.e01767.

16. Amjad M, Badshah S, Ahmad S, Badshah M, Jan S, Yasir M, Akram W, Shah IA, Muhammad R, Khan MI, Yasmeen T (2024). Finite element modeling of stress distribution and safety factors in a Ti-27Nb alloy hip implant under real-world physiological loading scenarios. PLOS ONE, 19(8), e0300270. DOI: 10.1371/journal.pone.0300270.

17. Darwich A, Nazha H, Abbas W (2019). Numerical study of stress shielding evaluation of hip implant stems coated with composite (carbon/PEEK) and polymeric (PEEK) coating materials. Biomedical Research, 30(1). DOI: 10.35841/biomedicalresearch.30-18-1048.

18. Gok MG (2022). Static, fatigue and stress-shielding analysis of the use of different PEEK based materials as hip stem implants. International Polymer Processing, 37(2), 152-163. DOI: 10.1515/ipp-2021-4133.

19. Ceddia M, Trentadue B (2024). A review of carbon fiber-reinforced polymer composite used to solve stress shielding in total hip replacement. AIMS Materials Science, 11(3), 449-462. DOI: 10.3934/matersci.2024023.

20. Arabnejad S, Johnston B, Tanzer M, Pasini D (2017). Fully porous 3D printed titanium femoral stem to reduce stress-shielding following total hip arthroplasty. Journal of Orthopaedic Research, 35(8), 1774-1783. DOI: 10.1002/jor.23445.

21. Zhao L, Wang Y, Wang Q, Zhang Y, Yang G (2024). Optimization Design and SLM Manufacturing of Porous Titanium Alloy Femoral Stem. Materials, 17(19), 4896. DOI: 10.3390/ma17194896.

22. Tyagi SA, Manjaiah M (2023). Additive manufacturing of titanium-based lattice structures for medical applications – A review. Bioprinting, 30, e00267. DOI: 10.1016/j.bprint.2023.e00267.

23. Distefano F, Pasta S, Epasto G (2023). Titanium Lattice Structures Produced via Additive Manufacturing for a Bone Scaffold: A Review. Journal of Functional Biomaterials, 14(3), 125. DOI: 10.3390/jfb14030125.

24. Abu Qudeiri JE, Abdudeen A, Sahadevan MR, Padmanabhan MA (2024). Numerical investigation on the wear characteristics of hip implant under static loading. Heliyon, 10(4), e26151. DOI: 10.1016/j.heliyon.2024.e26151.

25. Babić M, Verić O, Božić Ž, Sušić A (2020). Finite element modelling and fatigue life assessment of a cemented total hip prosthesis based on 3D scanning. Engineering Failure Analysis, 113, 104536. DOI: 10.1016/j.engfailanal.2020.104536.

26. Bliss O, Swadener JG, Pierce G, Zidane I (2023). Finite element analysis of a stemmed hip prosthesis to reduce stress shielding in the proximal femur. Journal of Mechanical Engineering and Sciences, 17(1), 9349-9359. DOI: 10.15282/jmes.17.1.2023.5.0739.