Case Study
ISSN: 3051-8814
Journal homepage: https://www.harrisonacademicpress.com/index.php/FBEMD
Frontiers in Biomedical Engineering and Medical Devices

Harrison Academic Press

Flexible Electrode Arrays for Long-Term Neural Recording: A Biocompatibility and Signal Fidelity Study

Krajnc P[1*], Correia T[2] and Steiner S[3]

[1]*Department of Biomedical Engineering, University of Ljubljana, Ljubljana, Slovenia*
[2]*Department of Neuroscience, University of Lisbon, Lisbon, Portugal*
[3]*Department of Materials Science, University of Innsbruck, Innsbruck, Austria*

ABSTRACT

Background: Chronic intracortical recording has traditionally relied on rigid, silicon-based microelectrode arrays, whose large mechanical mismatch with brain tissue is linked to progressive gliosis, blood-brain barrier disruption, and declining signal quality. Objective: This narrative review synthesizes published evidence on flexible, mechanically compliant neural electrode arrays (polyimide, parylene-C, carbon fiber, mesh electronics, and PEDOT:PSS-coated designs) as alternatives to rigid arrays for long-term recording. Methods: Peer-reviewed studies reporting histological biocompatibility and chronic electrophysiological performance of flexible versus rigid neural electrodes in rodent, non-human primate, and early human contexts were identified and synthesized. Findings: Flexible and ultra-compliant probes consistently show reduced glial encapsulation, preserved neuronal density near the interface, and, in several studies, sustained impedance, signal-to-noise ratio, and single-unit yield over weeks to months longer than comparable rigid devices, though matched multi-year comparisons remain scarce. Conclusions: Reducing electrode-tissue mechanical mismatch is a central, evidence-supported strategy for improving chronic neural interface biocompatibility and signal fidelity, though insertion mechanics, connectorization, and long-term coating stability remain open engineering challenges.

Keywords: *flexible neural electrodes; chronic neural recording; foreign-body response; electrode-tissue biocompatibility; signal-to-noise stability*

Citation: Krajnc P, Correia T, Steiner S (2024) Flexible Electrode Arrays for Long-Term Neural Recording: A Biocompatibility and Signal Fidelity Study. Front Biomed Eng Med Devices, 2(2): 01-06.
DOI: 10.5281/zenodo.22501649

Corresponding Author: *Petra Krajnc*

E-mail Address: *petra.krajnc@universityofljubljana.edu*

Article History: *Received 9 July 2024 | Accepted 9 October 2024 | Published 30 December 2024*

Copyright: *© 2024 Petra Krajnc, et al. This is an open access article distributed under the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited (**https://creativecommons.org/licenses/by/4.0/**).*

Introduction

Chronic intracortical recording has long depended on rigid, silicon-based microelectrode arrays such as the Utah array, which enabled the first demonstrations of stable single-unit recording over days to weeks in animal models [1]. Clinical translation of these devices into brain-computer interfaces confirmed their utility but also exposed a persistent limitation: recorded unit yield and signal amplitude decline over months to years of implantation, and a substantial fraction of arrays fail outright from mechanical, material, or biological causes [2,3]. Post-mortem and longitudinal studies have converged on a common explanation. The elastic modulus of bulk silicon (roughly 150 GPa) is five to six orders of magnitude greater than that of brain tissue, and micromotion between a stiff shank and the surrounding parenchyma sustains a chronic foreign-body response dominated by reactive astrocytes, activated microglia, and a compacted glial sheath that electrically and physically isolates the electrode from nearby neurons [4,5]. Blood-brain barrier disruption at the implant site correlates directly with reduced recording performance, reinforcing the mechanical-injury hypothesis of chronic failure [6]. Reviews synthesizing this literature have repeatedly identified the reduction of chronic inflammation and gliosis as the central unmet requirement for biocompatible intracortical interfaces [7].

Over the past fifteen years, this understanding has motivated a shift toward mechanically compliant, "flexible" neural electrodes fabricated from polyimide, parylene-C, or ultrathin silicon/polymer composites, and toward mesh- or thread-like probes with effective bending stiffness approaching that of tissue itself [8,9,10]. In parallel, conducting-polymer coatings such as poly(3,4-ethylenedioxythiophene) (PEDOT) have been used to lower electrode impedance and improve charge-transfer characteristics without enlarging the geometric footprint of a contact [11,12]. Flexible, high-density arrays and organic bioelectronic materials more broadly have also enabled surface (electrocorticographic) and injectable mesh geometries that were previously impractical with rigid substrates [13,14,15].

This narrative review synthesizes published evidence comparing

flexible and rigid neural electrode technologies across two linked dimensions: histological biocompatibility (glial scarring, neuronal density near the interface, and blood-brain barrier integrity) and chronic signal fidelity (impedance stability, signal-to-noise ratio, and single-unit yield over weeks to years). We do not report new experimental data; rather, we integrate findings from primate, rodent, and early human studies to characterize where flexible arrays have measurably improved on rigid designs, where trade-offs remain (handling, insertion mechanics, connectorization), and what the trajectory of the field suggests for long-term neural interface reliability.

The stakes of this comparison extend beyond basic neuroscience. Intracortical brain-computer interfaces intended for long-term clinical use must sustain decodable neural signals over years, not weeks, and every mechanical or biological source of signal attrition compounds the practical burden of recalibration, electrode replacement, or revision surgery placed on device users [3,16]. Understanding which specific material and geometric choices most reliably extend the useful lifetime of an implanted array is therefore a prerequisite for translating decades of primate and rodent electrophysiology into durable human neuroprosthetics.

Materials and Mechanical Design Strategies


The design space for flexible neural electrodes spans a continuum of substrate stiffness. Polyimide- and parylene-C-based shanks, tens of micrometers thick, retain sufficient column strength for manual or guided insertion while reducing bending stiffness by two to three orders of magnitude relative to bulk silicon [17,18]. At the extreme compliant end, sub-cellular-scale carbon fiber electrodes (6–8 µm diameter) and polymer nanoelectronic threads (cross-sections below 1 µm^2 in some designs) approach the mechanical compliance of individual axons, virtually eliminating the shear and micromotion forces thought to drive chronic gliosis [19,20,9]. Because such ultraflexible probes buckle under their own insertion force, practical implementation has required auxiliary strategies: temporary stiffening with dissolvable silk or PEG shuttles, coating with rigid biodegradable polymers, or syringe-injectable mesh electronics that self-expand from a folded state after delivery through a needle into the target tissue [10,21]. Mesh electronics scaled to 32–128 channels have demonstrated stable multi-week recordings in freely behaving rodents while occupying a tissue displacement volume far below that of a comparable silicon shank array [10].

Surface and epicortical geometries constitute a second major design branch. Actively multiplexed, foldable polyimide electrode arrays with hundreds of contacts have mapped high-resolution cortical activity in gyrencephalic brains without the tissue penetration required by intracortical designs [13]. Organic conducting-polymer electrodes, exemplified by the NeuroGrid platform, use PEDOT:PSS-coated conducting-polymer contacts on parylene substrates thin enough to conform to the pial surface, enabling recording of both local field potentials and, in a subset of channels, individual action potentials from the cortical surface [14]. Beyond the brain, electronic dura mater ("e-dura") implants employing stretchable gold conductors and PDMS substrates illustrate that comparable soft-electronics strategies extend to the spinal epidural space for combined electrical and pharmacological neuromodulation [22]. Across these platforms, the guiding materials principle—articulated in recent reviews of chronic bioelectronic interfaces—is to match the mechanical, and where possible the chemical, environment of the device to that of neural tissue rather than to prioritize substrate rigidity for ease of fabrication and handling [23,12].

Table 1: Representative flexible and rigid neural electrode platforms and reported chronic biocompatibility/mechanical characteristics.

Platform / Substrate	Typical Feature Scale	Reported Chronic Tissue Response	Key Reference
Bulk silicon (Utah array)	80-100 µm shank	Dense glial sheath; frequent mechanical/insulation failure by 1-3 years	Barrese et al. 2013
Polyimide/parylene-C thin film	10-20 µm thick	Reduced gliosis vs. silicon; requires insertion shuttle	Lecomte et al. 2018
Ultraflexible polymer thread	<1 µm^2 cross-section	Near-baseline neuronal density; minimal astrocyte/microglia accumulation at 6 months	Luan et al. 2017
Syringe-injectable mesh electronics	Mesh, sub-cellular struts	GFAP/Iba1 near control levels at 8 weeks	Fu et al. 2017
Carbon fiber microelectrode	6-8 µm diameter	Reduced encapsulation; stable single units to ~1 year in favorable cases	Patel et al. 2016

Figure 1: Illustrative bending stiffness ranges (log scale, typical reported values) for bulk silicon shanks, thin-film polyimide/parylene-C probes, PEDOT:PSS-coated organic electrodes, and ultraflexible carbon-fiber/mesh-electronics threads, spanning roughly five to six orders of magnitude and underlying the mechanical-mismatch hypothesis of chronic gliosis [8,9,10,17].



This shift has not eliminated engineering trade-offs; it has relocated them. Reducing shank stiffness improves compliance with tissue but degrades the column strength needed for unassisted penetration of the pia and cortex, so ultraflexible designs typically require a rigid or biodegradable shuttle, a stiffening coating that softens after implantation, or a fluidic delivery method such as syringe injection [10,21,17]. Connectorization is a second recurring constraint: as channel counts scale into the hundreds or thousands, the interconnects and packaging linking a flexible shank to rigid downstream electronics can dominate the overall device footprint and become a preferential site of chronic failure, a concern raised explicitly in comprehensive materials roadmaps for neural interface design [18,24]. These constraints explain why flexible-electrode research has proceeded materials family by materials family—polyimide and parylene shanks, carbon fiber and polymer threads, mesh electronics, and organic conducting-polymer coatings—rather


than converging immediately on a single dominant substrate.

Biocompatibility and Chronic Signal Fidelity

Histological comparisons directly attribute much of the reduced foreign-body response of flexible probes to lowered mechanical mismatch. Ultraflexible nanoelectronic threads implanted in mouse cortex showed neuronal density near the probe surface statistically indistinguishable from that of undisturbed tissue at six months, alongside minimal astrocytic and microglial accumulation—an outcome the authors described as "glial scar–free" integration, in contrast to the dense encapsulation typically seen around stiff silicon shanks [9]. Syringe-injectable mesh electronics produced comparably low chronic immune markers, with glial fibrillary acidic protein and Iba1 (microglial) staining near control tissue levels out to at least eight weeks post-implantation [10]. Composite microelectrodes coated with bioactive, cell-adhesive polymers similarly reduced the density of activated microglia at the tissue-electrode interface relative to uncoated silicon controls, indicating that surface chemistry and bulk mechanics act as complementary levers on the same inflammatory cascade [8]. These findings extend the broader histopathological literature establishing that reactive gliosis, blood-brain barrier compromise, and progressive neuronal loss are the dominant drivers of intracortical recording decline, rather than electronic component failure alone [4,5,6].

Chronic signal-fidelity data reinforce the histological picture, though direct head-to-head comparisons under matched conditions remain limited. Long-term studies of Utah-array-type silicon devices in non-human primates report a substantial fraction of arrays experiencing significant unit-yield decline or full failure within one to three years, with mechanical fracture, biological encapsulation, and insulation breakdown identified as the principal failure modes [2]. Chronic impedance spectroscopy on silicon arrays shows impedance magnitudes rising over the initial weeks after implantation before partially stabilizing, tracking the maturation of the glial sheath [25]. PEDOT-coated silicon electrodes, by contrast, maintain lower and more stable impedance across chronic recording windows, consistent with improved charge-transfer capacity at the electrode-tissue interface [11]. Carbon fiber microelectrode arrays and ultraflexible threads have both demonstrated recording of well-isolated single units with peak-to-peak amplitudes and signal-to-noise ratios sustained, in favorable cases, for several months to roughly a year, exceeding typical amplitude retention windows reported for comparably sized rigid microwires [20,19,9]. Surface arrays such as NeuroGrid similarly preserve stable local-field and spike-band signal quality over weeks of recording without penetrating the parenchyma at all [14]. High-channel-count flexible thread arrays intended for human brain-computer interfaces, described in white-paper form by Neuralink, and emerging comprehensive reviews of intracortical microelectrode design both frame long-term signal stability, rather than initial channel count, as the central unresolved engineering target for the field [16,24].

Figure 2: Reported approximate retention of chronic single-unit signal-to-noise ratio at one year post-implantation for representative rigid and flexible electrode platforms, illustrating typical ranges drawn from cited chronic recording studies rather than a single controlled comparison [2,20,19,9].



Taken together, the impedance, yield, and amplitude trends reported across these studies point to a consistent mechanism linking the two halves of this review: chronic signal degradation on rigid shanks tracks the time course of glial encapsulation and blood-brain barrier compromise, while flexible and ultra-compliant designs that limit that same tissue injury also tend to report the most favorable long-term recording metrics [6,5,9]. This correspondence, more than any single device metric in isolation, is the strongest argument in the published literature for mechanical compliance as a design priority rather than a secondary refinement.

Conclusion

Convergent histological and electrophysiological evidence supports the hypothesis that reducing the mechanical mismatch between neural electrodes and brain tissue—through thin-film polymer shanks, sub-cellular carbon or polymer threads, mesh electronics, or conformal surface arrays—measurably attenuates the chronic foreign-body response and, in several directly reported cases, extends the window of stable, high-fidelity recording relative to rigid silicon devices [9,10,8]. The benefit is not unconditional: flexible probes introduce their own engineering challenges, including insertion-aid requirements, connectorization at high channel counts, and, for organic conducting-polymer coatings, long-term material stability under repeated charge cycling [18,12]. Rigorous, matched comparisons of flexible and rigid arrays within single studies, particularly across multi-year timescales and in non-human primate models most relevant to eventual clinical translation, remain comparatively scarce [2,24]. As flexible substrate materials, ultra-compliant threads, and low-impedance coatings continue to mature alongside higher-channel-count fabrication methods, the balance of published evidence suggests that biocompatibility gains at the tissue-electrode interface are the most direct route toward the multi-year recording stability required for durable, high-fidelity neural interfaces [23,16].

Several priorities follow directly from the gaps identified above. First, the field would benefit from standardized, multi-year chronic studies that place flexible and rigid arrays side by side within the same animals and recording paradigms, since most current comparisons draw on separate cohorts, species, and recording hardware [2,24]. Second, insertion and connectorization strategies for ultra-compliant probes need continued refinement so that the biocompatibility advantages

demonstrated at the single-shank scale translate to the high channel counts required for clinically meaningful decoding [10,18]. Finally, closer integration of histological outcome measures with in vivo impedance and signal-to-noise tracking—rather than reporting these metrics in separate literatures—would sharpen the mechanistic link between tissue response and electrical performance that this review has argued is central to chronic device reliability [6,25]. Progress on these fronts, building on the material and geometric innovations surveyed here, will determine how quickly flexible electrode arrays move from demonstrated laboratory advantage to routine long-term clinical use.

Acknowledgements

The authors thank colleagues at Department of Biomedical Engineering, University of Ljubljana, Ljubljana, Slovenia, Department of Neuroscience, University of Lisbon, Lisbon, Portugal, and Department of Materials Science, University of Innsbruck, Innsbruck, Austria for helpful discussions during preparation of this review.

Funding

This research received no specific grant from any funding agency in the public, commercial, or not-for-profit sectors.

Conflict of Interest

The authors declare no conflict of interest.

Author Contributions

Krajnc P conceived the review, conducted the literature search, and drafted the manuscript. Correia T contributed to the literature screening and technical framing and critically revised the manuscript for important intellectual content. Steiner S contributed additional context and approved the final version for submission.

Ethics Statement

Not applicable. This is a narrative review of previously published literature and did not involve new experimental data, human participants, or animal subjects.

Data Availability

No new data were generated or analyzed for this review. All sources synthesized are cited in the reference list and are available through their original publishers.

Table 2: Reported chronic electrophysiological performance metrics across electrode platforms.

Platform	Chronic Impedance Trend	Signal Retention Window (Reported)	Key Reference
Silicon microelectrode array	Rises over initial weeks, partially stabilizes	Unit yield declines significantly by 1-3 years in many arrays	Prasad & Sanchez 2012; Barrese et al. 2013
PEDOT-coated silicon	Lower and more stable vs. uncoated	Improved charge-transfer stability across chronic windows	Ludwig et al. 2006
Carbon fiber array	Comparatively stable	Well-isolated units reported to ~1 year in favorable cases	Patel et al. 2016; Guitchounts et al. 2013
Ultraflexible nanoelectronic thread	Stable, low drift	Reliable recordings reported over several months to 6+ months	Luan et al. 2017
Surface PEDOT:PSS array (NeuroGrid)	Stable across recording weeks	Local field and spike-band signals preserved over weeks	Khodagholy et al. 2015

References

1. Rousche PJ, Normann RA (1998). Chronic recording capability of the Utah Intracortical Electrode Array in cat sensory cortex. Journal of Neuroscience Methods, 82(1), 1-15. DOI: 10.1016/S0165-0270(98)00031-4.

2. Barrese JC, Rao N, Paroo K, Triebwasser C, Vargas-Irwin C, Franquemont L, Donoghue JP (2013). Failure mode analysis of silicon-based intracortical microelectrode arrays in non-human primates. Journal of Neural Engineering, 10(6), 066014. DOI: 10.1088/1741-2560/10/6/066014.

3. Chestek CA, Gilja V, Nuyujukian P, Foster JD, Fan JM, Kaufman MT, Churchland MM, Rivera-Alvidrez Z, Cunningham JP, Ryu SI, Shenoy KV (2011). Long-term stability of neural prosthetic control signals from silicon cortical arrays in rhesus macaque motor cortex. Journal of Neural Engineering, 8(4), 045005. DOI: 10.1088/1741-2560/8/4/045005.

4. Polikov VS, Tresco PA, Reichert WM (2005). Response of brain tissue to chronically implanted neural electrodes. Journal of Neuroscience Methods, 148(1), 1-18. DOI: 10.1016/j.jneumeth.2005.08.015.

5. Salatino JW, Ludwig KA, Kozai TDY, Purcell EK (2017). Glial responses to implanted electrodes in the brain. Nature Biomedical Engineering, 1(11), 862-877. DOI: 10.1038/s41551-017-0154-1.

6. Nolta NF, Christensen MB, Crane PD, Skousen JL, Tresco PA (2015). BBB leakage, astrogliosis, and tissue loss correlate with silicon microelectrode array recording performance. Biomaterials, 53, 753-762. DOI: 10.1016/j.biomaterials.2015.02.081.

7. Jorfi M, Skousen JL, Weder C, Capadona JR (2015). Progress towards biocompatible intracortical microelectrodes for neural interfacing applications. Journal of Neural Engineering, 12(1), 011001. DOI: 10.1088/1741-2560/12/1/011001.

8. Kozai TDY, Langhals NB, Patel PR, Deng X, Zhang H, Smith KL, Lahann J, Kotov NA, Kipke DR (2012). Ultrasmall implantable composite microelectrodes with bioactive surfaces for chronic neural interfaces. Nature Materials, 11(12), 1065-1073. DOI: 10.1038/nmat3468.

9. Luan L, Wei X, Zhao Z, Siegel JJ, Potnis O, Tuppen CA, Lin S, Kazmi S, Fowler RA, Holloway S, Dunn AK, Chitwood RA, Xie C (2017). Ultraflexible nanoelectronic probes form reliable, glial scar-free neural integration. Science Advances, 3(2), e1601966. DOI: 10.1126/sciadv.1601966.

10. Fu TM, Hong G, Viveros RD, Zhou T, Lieber CM (2017). Highly scalable multichannel mesh electronics for stable chronic brain electrophysiology. Proceedings of the National Academy of Sciences, 114(47), E10046-E10055. DOI:

10.1073/pnas.1717695114.

11. Ludwig KA, Uram JD, Yang J, Martin DC, Kipke DR (2006). Chronic neural recordings using silicon microelectrode arrays electrochemically deposited with a poly(3,4-ethylenedioxythiophene) (PEDOT) film. Journal of Neural Engineering, 3(1), 59-70. DOI: 10.1088/1741-2560/3/1/007.

12. Rivnay J, Inal S, Salleo A, Owens RM, Berggren M, Malliaras GG (2018). Organic electrochemical transistors. Nature Reviews Materials, 3, 17086. DOI: 10.1038/natrevmats.2017.86.

13. Viventi J, Kim DH, Vigeland L, Frechette ES, Blanco JA, Kim YS, Avrin AE, Tiruvadi VR, Hwang SW, Vanleer AC, Wulsin DF, Davis K, Gelber CE, Palmer L, Van der Spiegel J, Wu J, Xiao J, Huang Y, Contreras D, Rogers JA, Litt B (2011). Flexible, foldable, actively multiplexed, high-density electrode array for mapping brain activity in vivo. Nature Neuroscience, 14(12), 1599-1605. DOI: 10.1038/nn.2973.

14. Khodagholy D, Gelinas JN, Thesen T, Doyle W, Devinsky O, Malliaras GG, Buzsaki G (2015). NeuroGrid: recording action potentials from the surface of the brain. Nature Neuroscience, 18(2), 310-315. DOI: 10.1038/nn.3905.

15. Kim DH, Lu N, Ma R, Kim YS, Kim RH, Wang S, Wu J, Won SM, Tao H, Islam A, Yu KJ, Kim TI, Chowdhury R, Ying M, Xu L, Li M, Chung HJ, Keum H, McCormick M, Liu P, Zhang YW, Omenetto FG, Huang Y, Coleman T, Rogers JA (2011). Epidermal Electronics. Science, 333(6044), 838-843. DOI: 10.1126/science.1206157.

16. Musk E, Neuralink (2019). An integrated brain-machine interface platform with thousands of channels. Journal of Medical Internet Research, 21(10), e16194. DOI: 10.2196/16194.

17. Lecomte A, Descamps E, Bergaud C (2018). A review on mechanical considerations for chronically-implanted neural probes. Journal of Neural Engineering, 15(3), 031001. DOI: 10.1088/1741-2552/aa8b4f.

18. Fattahi P, Yang G, Kim G, Abidian MR (2014). A review of organic and inorganic biomaterials for neural interfaces. Advanced Materials, 26(12), 1846-1885. DOI: 10.1002/adma.201304496.

19. Guitchounts G, Markowitz JE, Liberti WA, Gardner TJ (2013). A carbon-fiber electrode array for long-term neural recording. Journal of Neural Engineering, 10(4), 046016. DOI: 10.1088/1741-2560/10/4/046016.

20. Patel PR, Zhang H, Robbins MT, Nofar JB, Marshall SP, Kobylarek MJ, Kozai TDY, Kotov NA, Chestek CA (2016). Chronic in vivo stability assessment of carbon fiber microelectrode arrays. Journal of Neural Engineering, 13(6), 066002. DOI: 10.1088/1741-2560/13/6/066002.

21. Liu J, Fu TM, Cheng Z, Hong G, Zhou T, Jin L, Duvvuri M, Jiang Z, Kruskal P, Xie C, Suo Z, Fang Y, Lieber CM (2015). Syringe-injectable electronics. Nature Nanotechnology, 10(7), 629-636. DOI: 10.1038/nnano.2015.115.

22. Minev IR, Musienko P, Hirsch A, Barraud Q, Wenger N, Moraud EM, Gandar J, Capogrosso M, Milekovic T, Asboth L, Torres RF, Vachicouras N, Liu Q, Pavlova N, Duis S, Larmagnac A, Voros J, Micera S, Suo Z, Courtine G, Lacour SP (2015). Electronic dura mater for long-term multimodal neural interfaces. Science, 347(6218), 159-163. DOI: 10.1126/science.1260318.

23. Song E, Li J, Won SM, Bai W, Rogers JA (2020). Materials for flexible bioelectronic systems as chronic neural interfaces. Nature Materials, 19(6), 590-603. DOI: 10.1038/s41563-020-0679-7.

24. Wang Y, Yang X, Zhang X, Wang Y, Pei W (2023). Implantable intracortical microelectrodes: reviewing the present with a focus on the future. Microsystems & Nanoengineering, 9, 7. DOI: 10.1038/s41378-022-00451-6.

25. Prasad A, Sanchez JC (2012). Quantifying long-term microelectrode array functionality using chronic in vivo impedance testing. Journal of Neural Engineering, 9(2), 026028. DOI: 10.1088/1741-2560/9/2/026028.